

2 AUG 2004

PA 1194253

REC'D 10 AUG 2004

PCT

THE UNITED STATES OF AMERICA**TO ALL TO WHOM THESE PRESENTS SHALL COME:****UNITED STATES DEPARTMENT OF COMMERCE****United States Patent and Trademark Office**


July 15, 2004

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE UNDER 35 USC 111.**

APPLICATION NUMBER: 60/543,387**FILING DATE: February 11, 2004**

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

**By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS**



G. Montgomery
W. MONTGOMERY
Certifying Officer

PATENT APPLICATION SERIAL NO. _____

U.S. DEPARTMENT OF COMMERCE
PATENT AND TRADEMARK OFFICE
FEE RECORD SHEET

02/17/2004 EHAILE1 00000030 60543387

01 FC:1005 160.00 OP

PTO-1556
(5/87)

13281 U.S. PTO
021104

PROVISIONAL PATENT APPLICATION

OLIFF & BERRIDGE, PLC
P.O. Box 19928
Alexandria, Virginia 22320
Telephone: (703) 836-6400
Facsimile: (703) 836-2787

ATTORNEY DOCKET NO.: 118648

DATE: February 11, 2004

MAIL STOP PROVISIONAL PATENT APPLICATION

Customer Number: 25944

**PROVISIONAL PATENT APPLICATION
RULE §1.53(c)**

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

22858 U.S. PTO
60/543387

021104

Sir:

Transmitted herewith for filing under 37 CFR §1.53(c) is the provisional patent application of

FIRST INVENTOR: Richard Hendrikus Gerrit BRINKHUIS

RESIDENCE: Zwolle, The Netherlands
(City and Either State or Foreign Country)

SECOND INVENTOR: Rdolf Anthonius Maria VENDERBOSCH

RESIDENCE: Duiven, The Netherlands
(City and Either State or Foreign Country)


THIRD INVENTOR: _____

RESIDENCE: _____
(City and Either State or Foreign Country)

FOR (TITLE): AMINO ACID DERIVATIVES AND THEIR USE AS A SAG CONTROL AGENT

- ☐ Formal drawings (Figs. ____; sheets ____) are attached.
☒ This patent application is assigned to AKZO NOBEL N.V..
☐ The executed Assignment is filed herewith.
☐ Entitlement to small entity status is hereby asserted.
☒ Check No. 150938 in the amount of ☐ \$80.00 ☒ \$160.00 to cover the filing fee is attached.
Except as otherwise noted herein, the Commissioner is hereby authorized to charge payment of any additional filing fees required under 37 C.F.R. §1.16 or credit any overpayment to Deposit Account No. 15-0461. Two duplicate copies of this sheet are attached.

Respectfully submitted,


William P. Berridge
Registration No. 30,024

Joel S. Armstrong
Registration No. 36,430

WPB:JSA/tmw

OLIFF & BERRIDGE, PLC

ATTORNEYS AT LAW

Application Data Sheet

Application Information

Application Type:: Provisional
Subject Matter:: Utility
CD-ROM or CD-R: None
Title:: AMINO ACID DERIVATIVES AND THEIR USE AS A
SAG CONTROL AGENT
Attorney Docket Number:: 118648
Small Entity:: No

Applicant Information

Applicant Authority type:: Inventor
Primary Citizenship Country:: The Netherlands
Status:: Full Capacity
Given Name:: Richard
Middle Name:: Hendrikus Gerrit
Family Name:: BRINKHUIS
Name Suffix::
City of Residence:: Zwolle
State or Province of Residence::
Country of Residence:: The Netherlands

Applicant Authority type:: Inventor
Primary Citizenship Country:: The Netherlands
Status:: Full Capacity
Given Name:: Rudolf
Middle Name:: Anthonius Maria
Family Name:: VENDERBOSCH
City of Residence:: Duiven
Country of Residence:: The Netherlands

Correspondence Information

Correspondence Customer Number:: 25944

Assignee Information	
Assignee Name::	AKZO NOBEL N.V.
Street of mailing address::	Velperweg 76
City of mailing address::	Arnhem
Country of mailing address::	THE NETHERLANDS
Postal or Zip Code of mailing address::	6824 BM

AMINO ACID DERIVATIVES AND THEIR USE AS A SAG CONTROL AGENT

The invention relates to the use as sag control agent (SCA) in coating
5 compositions of rheology modification agents obtainable by reacting one or more
polyisocyanates with one or more optically active amino acid derivatives.

Bis-urea-type gelation agents based on diisocyanate and amino acids have been
mentioned in the literature. For example, L.A. Estroff and A.D. Hamilton in *Angew.*
10 *Chem. Int. Ed.*, 2000, Vol. 39, No.19, pp. 3447-3450, disclose bis-urea-type
hydrogelators based on a linear alkyl diisocyanate and L-glutamic acid monoester.
Similarly, A.J. Carr, R. Melendez, S.J. Geib, and A.D. Hamilton in *Tetrahedron*
Letters, 1998, Vol. 39, pp. 7447-7450, disclose bis-urea-type gelators based on
xylylene-1,4-diisocyanates and tert-butyl esters of L-alanine, L-phenylalanine, and L-
15 valine. These bis-urea compounds form gels in a variety of organic solvents.

The use of SCAs in coating compositions is also well-known. For example, US
4,311,622 discloses thixotropic coating compositions prepared from a binder and a
sag control agent which is the reaction product of a diisocyanate and a mono-
20 amine or hydroxy monoamine. Similarly, EP-A-0 261 863 discloses fluidity
controlling agents for paints which give thixotropic properties to a coating film when
it is applied to the paint and produce hardly any sagging in the formation of thick
coating films.

25 The demands for successful use of a rheology modification agent as sag control
agent in coating compositions are extensive. Preferably, a sag control agent is
able to combine low viscosities at high and medium shear stress (>5Pa) with high
viscosity at shear stresses corresponding to those created by gravity in wet coating

layers on non-horizontal substrates ($<1\text{Pa}$), the thixotropic character needs to show a time-dependent viscosity recovery after spraying in a specific window in order to combine effective anti-sagging behaviour with good levelling performance, and the variation of this character with solvent level, layer thickness or substrate angle with the vertical needs to be favourable to create robustness with respect to the sag-levelling balance. When the rheological structure is cured in a coating formulation, its stability must be maintained in the curing cycle, so as to maintain good control over sagging while allowing the best overall levelling. The amount of solvent needed to allow application, e.g. by spraying, should not be raised excessively by the presence of a sag control agent. Moreover, any rheology controlling agent used must have a rheological performance that allows storage over time without irreversible change.


Apart from the rheological performance, also the optical performance (the effect on coating appearance other than through sagging or levelling) is of utmost importance. This implies that any sag control additive must be fine enough not to create any visible disturbance (like protruding out of the film) when applied in thin films. Especially for clear coat applications, it also implies that no detectable haze or turbidity should be present after completion of the curing cycle, and also that no colour formation should have resulted from its presence. Again, also these characteristics should not change irreversibly with storage time. Of course, in order to limit costs and not interfere with other coating properties, efficient sag control agents that can do their job at low concentrations would be preferred.

Though many rheology control agents are known, few can fulfil all the demands listed above. Especially for applications in coating compositions in which relatively low curing temperatures (e.g. below 100°C) are used and formulations that do not contain formaldehyde derived curing agents or additives (as, e.g., in broadly used

isocyanate-polyol curing systems or systems based on acryloyl-functional resins to be cured through radical chemistry), there is a need for good sag control agents combining efficient anti-sagging behaviour with perfect optical properties.


- 5 Surprisingly, we have found that a specific class of urea compounds is able to deliver the rheological and optical performance over a wide temperature range that is needed for use as an SCA in coating compositions.

- 10 Accordingly, the present invention relates to the use as an SCA in coating compositions of a rheology modification agent obtainable by reacting one or more polyisocyanates with one or more optically active amino acids, esters and/or salts



- thereof of the formula (I) , not being a racemic mixture, wherein each of R₁, R₂, and R₃ is independently selected from hydrogen and linear, cyclic, or branched, substituted or unsubstituted, saturated or unsaturated hydrocarbyl, with
15 each of R₁ and R₂ being different such that the carbon atom C* is a chiral centre. Hereinafter, "amino acids, esters and/or salts thereof" are also referred to as "amino acid derivatives".

- By the feature "use as an SCA in coating compositions" is meant a method to make
20 coating compositions having the desired sag control properties involving the step of incorporating a rheology modification agent of the present invention. Preferably, the SCA that is used in said step is a rheology modification agent obtainable by reacting a conventional polyisocyanate with an optically active amino acids ester of the




formula (I) , wherein R₁, R₂, and R₃ are as defined above.

Particularly preferred SCAs according to the first embodiment of the invention are obtained if one or more optically active amino acid derivatives are reacted with one or more polyisocyanates selected from the group consisting of substituted or unsubstituted linear aliphatic polyisocyanates with an even number of carbon atoms in the chain between two isocyanate groups (as well as their dimeric derivatives such as uretdiones and corresponding trimeric isocyanurates or biurets), substituted or unsubstituted aryl, aralkyl, and cyclohexylene polyisocyanates.

10

Optionally, one or more additional compounds that may influence the crystallisation properties of the final product, such as reactive amino acid derivatives that are not of formula (I) and/or other amines, may be present during the reaction to prepare a rheology modification agent for use as an SCA.

15 Particularly preferred amino acid derivatives that are not of formula (I) are



20 The use of the prefix "poly" for polyisocyanates indicates that at least two of the mentioned functionalities are present in the respective "poly" compound. It is noted that when a polyurea product, i.e. the reaction product of amino acid esters with a polyisocyanate, is prepared, it is preferred to prepare a diurea or a triurea product.

In a preferred embodiment of the invention wherein polyurea products are prepared, it is possible to prepare polyurea products with the general formulae $X\text{-[urea-chiral centre]}_n$, X being the linking group of the molecule and n being the number of [urea-chiral centre] moieties (n is 2 or more), preferably wherein n is 2-5, more preferably wherein n is 2 or 3, most preferably wherein n is 2.

It is noted that in this description the general term "rheology modification agent(s)" is used to indicate suitable rheology modification agents for use as an SCA in coating compositions.

It is also noted that although at least one optically active amino acid derivative is used, the final reaction product obtained is not necessarily optically active. The final product may be in the d-, l- and/or meso-form.

If R_1 and/or R_2 of formula (I) is a hydrocarbyl, the hydrocarbyl is preferably independently selected from the group consisting of linear, cyclic or branched, substituted or unsubstituted, saturated or unsaturated, optionally hetero atom-containing $C_1\text{-}C_{24}$ alkyl, aryl, aralkyl, and alkenyl, fulfilling the above-mentioned provisos, more preferably selected from the group consisting of linear or branched $C_1\text{-}C_{24}$ alkyl, even more preferably from the group consisting of linear or branched $C_1\text{-}C_4$ alkyl, and most preferably the hydrocarbyl is a methyl or ethyl group.

In a preferred embodiment, one of R_1 and R_2 is hydrogen and the other is a hydrocarbyl selected from one of the above-indicated $C_1\text{-}C_{25}$ groups. If R_1 and/or R_2 is a hetero atom-containing $C_1\text{-}C_{25}$ group, it is preferably in the form of an ether unit. Optionally, R_1 and R_2 can be taken together with the chiral carbon atom C^* to which they are attached and form a substituted or unsubstituted ring containing 4 to 8

carbon atoms, provided that said ring is such that chirality at the carbon atom C* is maintained.

If present, the substituents on R₁ and/or R₂ and on the above-mentioned ring are preferably selected from the group consisting of alkyl, aryl, alkoxy, hydroxy, (preferably non-primary) amine, carboxylic acid, ester, phosphonic acid, phosphonic ester, keto, ketimine, urethane, allophanate, amide, thiol, imidazole, indole, guanidine, alkyl sulphide, and urea groups, most preferably from alkyl or alkoxy groups.

10

If R₃ is a hydrocarbyl as defined above, it is preferably selected from the group consisting of linear, cyclic or branched, substituted or unsubstituted, saturated or unsaturated, optionally hetero atom-containing C₁-C₂₅ alkyl, aryl, aralkyl, and alkenyl; more preferably, R₃ is selected from the group consisting of linear or branched, substituted or unsubstituted, optionally hetero atom-containing C₁-C₂₅ alkyl, even more preferably from the group consisting of linear or branched, substituted or unsubstituted C₁-C₈ alkyl, ether and/or, optionally esterified C₁-C₈ (poly)alkoxy, and most preferably from the group consisting of linear C₁-C₄ alkyl and, optionally alkoxylated, linear C₁-C₄ alkoxy. If alkoxylated, it is preferred to use ethoxylated, propoxylated, and/or butoxylated compounds.







20


If present, the substituents on R₃ are preferably selected from the group consisting of monoether alcohol and alkoxylated compounds.

25


In a preferred embodiment the rheology modification agent according to the invention is obtained by reacting one or more polyisocyanates with one or more optically active amino acid derivatives of formula (I), preferably in their naturally

occurring configuration, selected from the group consisting of:







glutamic acid (Glu),




glutamine (Gln),




histidine (His),









homocysteine (Hcy),




isoleucine (Ile),




leucine (Leu),







serine (Ser),




threonine (Thr),



tryptophan (Trp),



tyrosine (Tyr),



valine (Val),

ester derivatives and salts thereof.

5 The polyisocyanates are preferably selected from the group consisting of aliphatic, cycloaliphatic, aralkylene, and arylene polyisocyanates, more preferably from the
10 group consisting of substituted or unsubstituted linear aliphatic polyisocyanates with an even number of carbon atoms in the chain between two isocyanate groups

(and their isocyanurates, biurets, uretdiones) and substituted or unsubstituted arylene, aralkylene, and cyclohexylene polyisocyanates. The polyisocyanate usually contains 2 to 40 and preferably 4 to 8 carbon atoms. The polyisocyanate preferably contains at most four isocyanate groups, more preferably at most three isocyanate groups, and most preferably two isocyanate groups. It is even more preferred to use a symmetrical aliphatic or cyclohexylene diisocyanate. Suitable examples of diisocyanates are preferably selected from the group consisting of tetramethylene-1,4-diisocyanate, hexamethylene-1,6-diisocyanate (HMDI), ω,ω' -dipropylether diisocyanate, thiodipropyl diisocyanate, trans-cyclohexyl-1,4-diisocyanate, dicyclohexylmethane-4,4'-diisocyanate, 1,5-dimethyl-(2,4- ω -diisocyanato methyl) benzene, 1,5-dimethyl(2,4- ω -diisocyanatoethyl) benzene, 1,3,5-trimethyl(2,4- ω -diisocyanato-methyl) benzene, 1,3,5-triethyl(2,4- ω -diisocyanato-methyl) benzene, meta-xylylene diisocyanate, para-xylylene diisocyanate, dicyclohexyl-dimethylmethane-4,4'-diisocyanate, 2,4-toluene diisocyanate, 2,6-toluene diisocyanate, and diphenylmethane-4,4'-diisocyanate (MDI). Further suitable polyisocyanates are preferably selected from the group consisting of polyisocyanates based on HMDI, including condensed derivatives of HMDI, such as uretdiones, biurets, isocyanurates (trimers), and asymmetrical trimers, etc., many of which are marketed as Desmodur[®] N and Tolonate[®] HDB and Tolonate[®] HDT, and polyisocyanates known as "polymeric MDI". Polymeric MDI typically is a mixture of pure MDI and oligomers of MDI. Particularly preferred polyisocyanates are selected from the group consisting of HMDI, its isocyanurate trimer, its biuret, trans-cyclohexyl-1,4-diisocyanate, meta-xylylene diisocyanate, and, toluene diisocyanate. Most preferably, HMDI is selected.

25

Substituted polyisocyanates are typically formed by reaction of linear polyisocyanates to form dimers and/or trimers.

As will be understood by the person skilled in the art, it is also possible to use conventionally blocked polyisocyanates which generate two or more isocyanates *in situ*, as long as the blocking agent, after splitting, does not prevent the formation of the rheology modification agent according to the invention. Throughout this document the term "polyisocyanate" is used to denominate all polyisocyanates and polyisocyanate-generating compounds.

It is noted that it is also possible to react one or more optically active amino acid derivatives with one or more optically active (poly)isocyanates. However, for economic reasons, such a process and the resulting rheology modification agents are less preferred.

In the reaction between the one or more isocyanates and the one or more amino acid derivatives for the preparation of the rheology modification agent it is preferred that either the isocyanate or the amino acid derivative is used in excess instead of using stoichiometric amounts. For example, the ratio of the number of amino groups of the amino acid derivative to the number of (generated) isocyanate groups may be in the range of 0.7 to 1.5. Preferably, the ratio is about 0.9 to 1.1.

It is to be understood that any non-racemic enantiomer mixture of chiral amino acid derivatives can be used to make a rheology modification agent according to the invention, provided that this mixture contains optically active amino acid derivative according to the invention. In this description the term "enantiomeric excess", hereinafter also referred to as "ee", is used to indicate the excess of one enantiomer over racemic material in a sample that comprises both enantiomers of the chiral compound. The enantiomeric excess is expressed as a percentage: A racemic sample, i.e. a 50:50 mixture of both enantiomers, has an ee of 0% and an

enantiomerically pure sample has an ee of 100%. It is noted that although use should not be made of a 50:50 ratio of two enantiomers, optimum results may very well be obtained when the ratio of two enantiomers is not 100:0. In other words, the ee of the enantiomeric mixture should not be 0%. The ee preferably is at least
5 10% (as in 55:45 ratio), more preferably at least 20% (as in 60:40 ratio), even more preferably at least 40% (as in 70:30 ratio), and most preferably at least 50% (as in 75:25 ratio).

10 In one embodiment of the invention preferably use is made of a mixture of enantiomers with an ee of at least 55%, most preferably at least 75%, since in this embodiment the use of significant enantiomeric excess of just one enantiomer, i.e. an ee of at least 55%, results in a rheology modification agent with improved rheology control properties.

15 The reaction between the isocyanate and the amino acid derivative can be carried out in any arbitrarily chosen way by combining the reaction components, optionally at elevated temperature, as will be clear to a person skilled in the art. It is preferred that the reaction is carried out at temperatures in the range of 0°C to 150°C, more particularly in the range of 20°C to 80°C. Although in general the reaction
20 components are combined in any arbitrarily chosen manner, preferably the isocyanate is added to the amino acid derivative, which may be done in several steps, if desired. Optionally, the reaction may be carried out in the presence of an inert solvent, for example acetone, methyl isobutyl ketone, N-methyl pyrrolidone, benzene, toluene, xylene, or an aliphatic hydrocarbon such as petroleum ether,
25 alcohols, and water, or mixtures thereof. Here the term "inert" indicates that the solvent does not interfere in the process of polyurea formation, which means that the amount of polyurea formed when solvent is present is at least 80% of the amount produced when no solvent is present.

- The preparation of the rheology modification agent optionally may also be carried out in the presence of a binder. This can be done by mixing a mixture of the binder and the isocyanate with the amino acid derivative or by mixing the isocyanates with
- 5 a mixture of the binder and the amino acid derivative, or by mixing two mixtures of binder with amino acid derivative and NCO, respectively. It will be obvious that if the binder is highly reactive with either the amino acid derivative or the isocyanate, the binder and that particular susceptible compound cannot be premixed. By the term "highly reactive" is meant here that more than 30% of the susceptible amino
- 10 acid derivative or isocyanate reacts with the binder before the amino acid derivative and the isocyanate are mixed in order to prepare the rheology modification agent. The mixing operation may be carried out in any convenient manner, with the reactants being vigorously stirred. Amino acid derivative may be added to isocyanate or isocyanate may be added to amino acid derivative,
- 15 whichever is most convenient. If a binder is used and either the amino acid derivative or the isocyanate is highly reactive with the binder, then the compound that is most reactive with the binder is preferably added to the mixture of the binder with the compound that is least reactive with the binder.
- 20 In one embodiment of the invention, the rheology modification agent is produced in the binder or curing component of the final coating composition in such a low concentration, preferably 0.1-8%, that the binder dispersion can still be handled as a fluid and can be subsequently used in the coating composition, optionally using further binder, curing component and/or other (conventional) additives. When the
- 25 rheology modification agent is produced in the binder, it is preferably prepared at a temperature in the range of 20-80°C, under adequate stirring.

- In another embodiment of the preparation of the rheology modification agent, the binder is mixed with such amounts of the isocyanate and the amino acid derivative that upon conclusion of the reaction a mixture is obtained as a solid-like material, which can be used as master batch of the rheology modification agent, consisting
- 5 of 5-99, preferably 6-50, more preferably 7-25, parts by weight of the rheology modification agent relative to 95-1, preferably 94-50, more preferably 93-75, parts by weight of the binder. Optionally, further diluents or adjuvants may be present. The binders in the final coating composition and in the master batch of the rheology modification agents may be of the same or different composition. The
- 10 preferred concentrates are suitably prepared in an atmosphere of inert gas at a temperature in the range of 20-80°C, with the amino acid derivative first being added to a binder material and, after the mixture has been homogenised, the isocyanate being slowly added to the mixture, with stirring.
- 15 Although it is less desired, binder or curing compositions comprising the rheology modification agent may also be prepared in the presence of said rheology modification agent or by preparing the binder or curing compound as well as the rheology modification agent at the same time. The skilled person will have no problem combining the rheology modification agent, or the starting materials for a
- 20 rheology modification agent, with the starting materials for the binder or curing compound, with subsequent reaction to form the rheology modification agent-containing binder or curing compositions.
- If the rheology modification agent is not prepared in the binder or curing
- 25 compound, it can be mixed, preferably as a concentrated solution, with one or more of the components of the coating composition, preferably the binder or any other liquid component, as a result of which a fine dispersion is obtained. The mixtures of the preferred embodiment preferably form a dispersion of the rheology

modification agent in the liquid component, such as the binder, which can be solventless, solvent based, or water based.

- When the rheology modification agent is used to formulate coating compositions, the resulting coating compositions show an improved rheology, here dubbed thixotropic, and may have an opaque, opalescent or even transparent appearance, depending on the size and the refractive index of the dispersed particles of the rheology modification agent.
- 10 Optionally, conventional additives may be present in any of the coating compositions of the present invention, such as solvent and/or dispersing additives, pigment dispersants, dyes, pigments, UV curing additives, flow additives, other rheology control additives, solvents, and accelerators for the curing reaction, for instance acidic compounds such as p-toluene sulphonic acid or blocked products thereof. The coating compositions may comprise other conventional rheology modification agents which may be solvent based or solventless. In another embodiment, the liquid other conventional rheology modification agents are water based.
- 20 The thixotropic coating compositions may be applied to a substrate in any desired manner, for instance by rolling, pneumatic or electrostatic spraying, brushing, sprinkling, casting, and dipping.
- 25 The degree to which the rheology of the compositions in which the present rheology modification agents are used is changed, depends, *inter alia*, on the proportion of rheology modification agent and the nature of the rheology modification agent and the components of the composition. As a rule, the desired degree of thixotropy may be obtained by employing the rheology modification

agent preferably in an amount of at least 0.01%, more preferably at least 0.05%, even more preferably at least 0.10%, and most preferably at least 0.15%, and preferably of at most 30%, more preferably at most 10%, even more preferably at most 3%, and most preferably at most 1.5%, based on the total weight of the composition.

The thixotropic compositions according to the invention may contain polar and/or non-polar solvents. Preferably, the thixotropy is present not only at room temperature but also at elevated temperature, so that the rheology modification agent according to the invention is suitable for use at room temperature and in baking paints (curing), for instance in the range of 50°C to 250°C, preferably less than 125°C, more preferably less than 100°C, over a period of 2 to 120 minutes.

The rheology modification agent used as an SCA according to the invention further has the considerable advantage that it does not or seldom decreases the gloss or brightness of the composition, especially for clear coats.

The rheology modification agents are preferably used in isocyanate based coating compositions, polyol based coating compositions, acryloyl based coating compositions, epoxy curable coating compositions, and dual curable coating compositions, the latter also referred to as hybrid curable coating compositions. A dual curable coating composition is, for example, a combination of a UV curable acryloyl based system and a chemically curable isocyanate based system, wherein the two curable systems may be cured in random order and the isocyanate may be cured at a temperature in the range of room temperature up to 140°C.

The rheology modification agents were found to be particularly suited to improve the rheology in conventional isocyanate-reactive two-component (2K) coating systems cured with one or more polyol compounds, thiol compounds and/or amine-functional compounds such as Desmophen[®] NH 1220, Desmophen[®] NH 1420, and Desmophen[®] NH 1521, at a temperature of at least 25°C and below 150°C, preferably below 125°C, more preferably below 100°C. In addition, the rheology modification agents were also found to be particularly suited to improve the rheology of formulations based on acryloyl-functional compounds cured in a conventional way, for example through a radical mechanism as in the case of most UV- or EB-curing formulations.

The invention is elucidated by the following examples.

Examples 1-3 and Comparative Example A

15	Setalux [®] 1767 VV-65	acrylic polyol ex Akzo Nobel
	Alanine butyl ester/HDI	Alanine butyl ester/hexamethylene diisocyanate
	Setal [®] 166 SS-80	polyester polyol ex Akzo Nobel
	Tinstab [®] BL 277	ex Akcros Chemicals
	Baysilon [®] OL-17	ex Bayer AG
20	Byk [®] 306	ex Byk-Cera BV
	Tinuvin [®] 1130	ex Ciba Specialty Chemicals
	Tinuvin [®] 292	ex Ciba Specialty Chemicals
	Tolonate [®] HDT 90	aliphatic poly-isocyanate ex Rhodia
	Vestanat [®] T1890	poly-isocyanate ex Huels

25

Four paint formulations (comparative formulation A and formulations 1-3 according to the invention) were prepared (see Table I). The paints were sprayed onto a

vertical tin-plated plate with 13 holes of 1 cm diameter and vertically baked at the indicated schedule. The sagging limit was determined as the layer thickness between the hole at which sagging occurs and the preceding hole. Another way to measure sagging is to measure the layer thickness at the point where the length of the tear is 1 cm.

These examples show that the rheology modification agent according to the invention has good activity as sag control agent and excellent transparency in the clear coats. Also at 24 min. 140°C, 60 min. 60°C, and drying for seven days at room temperature clear coats applied on glass are completely clear. The transmission (in %) of the clear coats on glass with a film thickness of 40 micron was measured using the ColorQuest spectrophotometer of Hunterlab. If the transmission values are mutually compared, a lower transmission value means more haze and less transparency.

Table I

Example	A	1	2	3
Setalux [®] 1767 VV-65	64.4	45.7	35.8	29.7
Alanine butyl ester/HDI in Setal [®] 166 SS-80	0	18.7	28.6	34.7
Tinstab BL 277 (1% in butyl acetate)	1.0	1.0	1.0	1.0
Baysilon OL-17 (2 % in butyl acetate)	3.0	3.0	3.0	3.0
Byk 306	0.5	0.5	0.5	0.5
Tinuvin 1130	1.5	1.5	1.5	1.5
Tinuvin 292	1.0	1.0	1.0	1.0
Tolonate HDT 90	25.0	25.0	25.0	25.0
Vestanat T1890	10.6	10.6	10.6	10.6
Thin down with butyl acetate to 28 s DIN cup 4/23 °C				
Theor. % RCA	0	0.70	1.00	1.30
Substrate: tin-plated steel, Stoving schedule: 45 min. 80 °C				
Sagging limit (micron)	50	61	75	76
Tears of 1 cm (micron)	61	85	103	106
Transmission (%)	78.2	78.2	77.8	78.3

Examples 4-18 and Comparative Examples B-D

- Setal[®] 166 SS-80 polyester polyol ex Akzo Nobel
- 5 Setalux[®] 1767 acrylic polyol ex Akzo Nobel
- Setalux[®] 1198 acrylic polyol ex Akzo Nobel
- Actilane[®] 890 melamine acrylate ex Akzo Nobel
- Resin X resin obtained as described in Example 3 of
WO02/098942

Tolonate [®] HDT-LV	aliphatic poly-isocyanate. ex Rhodia
HDI-BA	hexamethylene diisocyanate-benzyl amine
Amino acids	ex Aldrich

- 5 All SCAs were prepared *in situ* in the host resins mentioned (See Table II), in concentrations corresponding to 3.7wt% on solids. Coating compositions were formulated so as to obtain an SCA concentration of 1.0 to 1.2 wt%, based on total solids. For all NCO-polyol curing formulations, Tolonate[®] HDT-LV (Tol[®] HDT) was used as cross-linker in a 1:1 molar OH-NCO stoichiometry. Butyl acetate was used
- 10 to dilute the formulations in order to allow measurement of their rheology property at ca. 0.8 Pas high shear viscosity. All NCO formulations cured 30 minutes 60°C; Actilane[®] 890 cured at room temperature using UV light.

- The viscosities were measured with a cone and plate rheometer, in controlled shear stress mode, starting at high (1,000 Pa) shear stress. Compliance was
- 15 measured after high shear disturbance of the film, applying 0.5 Pa shear stress and monitoring cumulative movement as function of time. The first measurement gives a value illustrating equilibrium rheological structure, the second measurement explicitly takes into account the rate of structure recovery: low values indicate low cumulative flow.

Table II

Ex.	Amino acid	Ester	Host Resin	Cross-linker	$\eta(1\text{Pa})/\eta(1000\text{Pa})$	J (300s at 0.5 Pa) Pa^{-1}	Clarity after cure
B	β -alanine	Butyl	Setal [®] 166 SS-80	Tol [®] HDT	<2	n.d.	n.d.
C	D,L-aspartic (racemic)	Dibutyl	Setal [®] 166 SS-80	Tol [®] HDT	<2	n.d.	n.d.
D	Conventional SCA: HDI-BA		Setal [®] 166 SS-80	Tol [®] HDT	6	190	Hazy
4	L-phenylalanine	Butyl	Setal [®] 166 SS-80	Tol [®] HDT	5	120	Clear
5	L-phenylalanine	Methyl	Setal [®] 166 SS-80	Tol [®] HDT	>3800	30	Clear
6	L-phenylalanine	Methyl	Setalux [®] 1767	Tol [®] HDT	n.d. (high)	n.d.	Clear
7	L-alanine	Butyl	Setal [®] 166 SS-80	Tol [®] HDT	1000	8	Clear
8	L-alanine	Methyl	Setal [®] 166 SS-80	Tol [®] HDT	>3800	8	Clear
9	L-glutamic acid	Dibutyl	Setal [®] 166 SS-80	Tol [®] HDT	2	115	Clear
10	L-glutamic acid	Diethyl	Setal [®] 166 SS-80	Tol [®] HDT	130	38	Clear
11	L-glutamic acid	Dimethyl	Setal [®] 166 SS-80	Tol [®] HDT	4.5	61	Clear
12	L-glutamic acid	Dibutyl	Setalux [®] 1198	Tol [®] HDT	n.d. (high)	n.d.	Clear
13	L-aspartic	Dimethyl	Setal [®] 166 SS-80	Tol [®] HDT	4	61	Clear


14	L-aspartic		Dibutyl	Setal [®] 166 SS-80	Tol [®] HDT	440	3	Clear
15	L-aspartic		Di-n-octyl	Setal [®] 166 SS-80	Tol [®] HDT	2.5	145	Clear
16*	L-alanine		Butyl	Actilane [®] 890 + Actilane [®] 424	-	400	26	Clear
17	L-alanine		Butyl	Resin X	Tol [®] HDT	100	50	Clear
18	L-alanine		Butyl	Setalux [®] 1767	Tol [®] HDT	150	18	Clear

n.d. = not determined

* SCA prepared in Actilane[®] 890, formulated with Actilane[®] 424 to obtain 0.8Pas high shear viscosity: wt% SCA in this formulation 0.75 wt%. Cured at room temperature with photo initiator and UV-radiation.

Claims

1. Use as a sag control agent in a coating composition of a rheology modification agent obtainable by reacting one or more polyisocyanates with one or more optically active amino acids, esters and/or salts thereof of the general formula



(I) , not as racemic mixture, wherein each of R₁, R₂, and R₃ is independently selected from hydrogen and linear or branched, substituted or unsubstituted, saturated or unsaturated hydrocarbyl, with each of R₁ and R₂ being different such that the carbon atom C* is a chiral centre.


10

2. Use according to claim 1 wherein the one or more polyisocyanates are selected from the group consisting of substituted or unsubstituted linear aliphatic polyisocyanates with an even number of carbon atoms in the chain between two isocyanate groups (as well as condensed dimer and trimer derivatives as such uretdione, isocyanurate or biuret trimers) and substituted or unsubstituted arylene, aralkylene, and cyclohexylene polyisocyanates.







15


3. Use according to claim 1 or 2 wherein the one or more optically active amino acid acids and/or esters thereof of formula (I) are selected from the group of compounds consisting of:

20




alanine (Ala),







glutamine (Gln),




histidine (His),




homocysteine (Hcy),




isoleucine (Ile),




leucine (Leu),




lysine (Lys),




methionine (Met),




norleucine (Nle)




norvaline (Nva),







ornithine (Orn),



phenylalanine (Phe),



serine (Ser),



5 ester derivatives and salts thereof.

4. Use according to any one of claims 1-3 wherein if R₁ and/or R₂ is a hydrocarbyl independently selected from the group consisting of linear, cyclic or branched, substituted or unsubstituted, saturated or unsaturated, optionally hetero atom-containing, C₁-C₂₄ alkyl, aryl, aralkyl, and alkenyl, preferably the group
- 10 consisting of linear or branched C₁-C₂₄ alkyl, more preferably from the group consisting of linear or branched C₁-C₄ alkyl, and most preferably the hydrocarbyl is a methyl or ethyl group.

5. Use according to any one of claims 1-4 wherein if R_3 is a hydrocarbyl, the hydrocarbyl is selected from the group consisting of linear, cyclic or branched, substituted or unsubstituted, saturated or unsaturated, optionally hetero atom-containing C_1 - C_{25} alkyl, aryl, aralkyl, and alkenyl, more preferably R_3 is selected from the group consisting of linear or branched, substituted or unsubstituted, optionally hetero atom-containing C_1 - C_{25} alkyl, even more preferably from the group consisting of linear or branched, substituted or unsubstituted C_1 - C_8 alkyl, ether and/or, optionally esterified, C_1 - C_8 (poly)alkoxy, and most preferably from the group consisting of linear C_1 - C_4 alkyl and, optionally alkoxylated, linear C_1 - C_4 alkoxy.
6. Use according to any one of claims 1-5 wherein the coating composition is an isocyanate based coating composition.
7. Use according to any one of claims 1-5 wherein the coating composition is an acryloyl based coating composition.
8. Use according to any one of claims 1-5 wherein the coating composition is an epoxy curable coating composition.
9. Use according to any one of claims 1-5 wherein the coating composition is a dual curable coating composition.
10. Use according to any one of claims 1-5 wherein the coating composition is a conventional isocyanate-reactive two-component (2K) coating system that is cured with one or more polyol compounds, thiol compounds and/or amine-functional compounds, at a temperature of at least 25°C and below 150°C, preferably below 100°C.

11. Use according to any one of claims 1-10 further including the step of applying a coating film of the coating composition onto a substrate before said coating film is cured.
- 5 12. Coating compositions that are obtainable by using a rheology modification agent in accordance with any one of claims 1-11.

Abstract

The invention relates to the use as a sag control agent (SCA) in coating compositions of a rheology modification agent obtainable by reacting one or more
5 polyisocyanates with one or more derivatives of optically active amino acids.